

























Polybatch Material Standard Colors for Film Extrusion

Properties	Color	Heat stability ISO 12877-2	Light fastness ISO 4892-2	Weather Fastness ISO 4892-2	NIR Detectable	Specific Property Features	
<ul style="list-style-type: none"> Heat stability refers to 5% masterbatch addition in the respective carrier resin (ISO 12877-2, maximum color change of 4 according to Grey Scale ISO 105-A02, 5 minute dwell time) Light fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Blue Wool Scale ISO 102-B02, 8 = very good, 1 = very poor) Weather fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Grey Scale ISO 102-A02, 5 = very good, 1 = very poor) NIR Detectable refers to 2% masterbatch addition in the respective carrier resin (internal method, polymer identification by near infrared spectroscopy) Masterbatches with suffix E and ZA are not recommended for use in HDPE or PP Masterbatches with suffix E are not recommended for an addition rate lower than 2% and higher than 15%, they should also not be used in combination with UV stabiliser or calcium oxide desiccant Food contact - detailed information available on request 							
Standard Colors for Polyolefins - Based on polyethylene carrier resin							
Polybatch 2905 ZA		Yellow	240°C	7	2-3	Yes	
Polybatch 2057 E		Yellow	230°C	6	1	Yes	
Polybatch L 2904 ZA		Yellow	240°C	7	2-3	Yes	
Polybatch 2450 E/5		Yellow	230°C	6	1	Yes	
Polybatch L 2546		Yellow	300°C	6	2	Yes	Excellent heat stability alternative to yellow 'E' colors
Polybatch 2214 E/5		Yellow	230°C	6	1	Yes	
Polybatch 2028 E		Yellow	230°C	6	1-2	Yes	
Polybatch 1019 E		Orange	230°C	5	1	Yes	
Polybatch L 1014		Orange	290°C	7-8	1-2	Yes	Excellent heat stability alternative to orange 'E' colors
Polybatch 1900 E/5		Orange	230°C	4-5	1	Yes	
Polybatch 1046 E		Orange	230°C	5	1	Yes	
Polybatch L 1015 ZA		Orange	240°C	7	2	Yes	Higher light fastness alternative to orange 'E' colors
Polybatch 5020		Red	240°C	2-3	0-1	Yes	

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. Polybatch, Polyblak and Polywhite are trademarks owned and/or used by the LyondellBasell family of companies. Polybatch and Polyblak are registered in the U.S. Patent and Trademark Office.














Polybatch Material Standard Colors for Film Extrusion

Properties	Color	Heat stability ISO 12877-2	Light fastness ISO 4892-2	Weather Fastness ISO 4892-2	NIR Detectable	Specific Property Features	
<ul style="list-style-type: none"> Heat stability refers to 5% masterbatch addition in the respective carrier resin (ISO 12877-2, maximum color change of 4 according to Grey Scale ISO 105-A02, 5 minute dwell time) Light fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Blue Wool Scale ISO 102-B02, 8 = very good, 1 = very poor) Weather fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Grey Scale ISO 102-A02, 5 = very good, 1 = very poor) NIR Detectable refers to 2% masterbatch addition in the respective carrier resin (internal method, polymer identification by near infrared spectroscopy) Masterbatches with suffix E and ZA are not recommended for use in HDPE or PP Masterbatches with suffix E are not recommended for an addition rate lower than 2% and higher than 15%, they should also not be used in combination with UV stabiliser or calcium oxide desiccant Food contact - detailed information available on request 							
Polybatch L 5646		Red	300°C	8	4	Yes	Excellent heat stability and light fastness alternative for red
Polybatch 5330		Red	240°C	6	1	Yes	
Polybatch 5500		Red	240°C	5-6	1	Yes	
Polybatch 5505		Red	240°C	5-6	1	Yes	
Polybatch 5670		Red	240°C	6	1	Yes	
Polybatch 5246		Pink	260°C	6-7	1	Yes	
Polybatch 4022		Violet	240°C	6	2-3	Yes	
Polybatch 4300		Blue	280°C	8	5	Yes	
Polybatch 4012		Blue	290°C	8	4-5	Yes	
Polybatch L 4535		Blue	290°C	8	4-5	Yes	
Polybatch 4020		Blue	290°C	8	5	Yes	Transparent blue for tinted film
Polybatch 4021		Blue	300°C	8	4-5	Yes	
Polybatch 4025		Blue	300°C	8	4-5	Yes	

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. Polybatch, Polyblak and Polywhite are trademarks owned and/or used by the LyondellBasell family of companies. Polybatch and Polyblak are registered in the U.S. Patent and Trademark Office.














Polybatch Material Standard Colors for Film Extrusion

Properties	Color	Heat stability ISO 12877-2	Light fastness ISO 4892-2	Weather Fastness ISO 4892-2	NIR Detectable	Specific Property Features	
<ul style="list-style-type: none"> Heat stability refers to 5% masterbatch addition in the respective carrier resin (ISO 12877-2, maximum color change of 4 according to Grey Scale ISO 105-A02, 5 minute dwell time) Light fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Blue Wool Scale ISO 102-B02, 8 = very good, 1 = very poor) Weather fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Grey Scale ISO 102-A02, 5 = very good, 1 = very poor) NIR Detectable refers to 2% masterbatch addition in the respective carrier resin (internal method, polymer identification by near infrared spectroscopy) Masterbatches with suffix E and ZA are not recommended for use in HDPE or PP Masterbatches with suffix E are not recommended for an addition rate lower than 2% and higher than 15%, they should also not be used in combination with UV stabiliser or calcium oxide desiccant Food contact - detailed information available on request 							
Polybatch 4500		Blue	300°C	8	4-5	Yes	Transparent blue for tinted film
Polybatch 4656/5		Blue	300°C	8	5	Yes	
Polybatch 4358		Blue	290°C	8	5	Yes	
Polybatch 3000		Green	300°C	8	5	Yes	
Polybatch 3011 E		Green	230°C	6	1	Yes	
Polybatch L 3116		Green	250°C	7	2-3	Yes	Higher light fastness alternative to green 'E' colors
Polybatch 3012 E		Green	230°C	6	1	Yes	
Polybatch 3510 E		Green	230°C	6	1	Yes	
Polybatch L 3060		Green	250°C	7-8	4-5	Yes	Higher heat stability alternative to Polybatch 3600
Polybatch 3600		Green	200°C	7-8	4-5	Yes	
Polybatch 3015		Green	300°C	8	5	Yes	Transparent green for tinted film
Polybatch L 3888		Green	300°C	8	5	No	
Polybatch 9600		Ivory	300°C	8	5	Yes	

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. Polybatch, Polyblak and Polywhite are trademarks owned and/or used by the LyondellBasell family of companies. Polybatch and Polyblak are registered in the U.S. Patent and Trademark Office.











Polybatch Material Standard Colors for Film Extrusion

Properties	Color	Heat stability ISO 12877-2	Light fastness ISO 4892-2	Weather Fastness ISO 4892-2	NIR Detectable	Specific Property Features	
<ul style="list-style-type: none"> Heat stability refers to 5% masterbatch addition in the respective carrier resin (ISO 12877-2, maximum color change of 4 according to Grey Scale ISO 105-A02, 5 minute dwell time) Light fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Blue Wool Scale ISO 102-B02, 8 = very good, 1 = very poor) Weather fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Grey Scale ISO 102-A02, 5 = very good, 1 = very poor) NIR Detectable refers to 2% masterbatch addition in the respective carrier resin (internal method, polymer identification by near infrared spectroscopy) Masterbatches with suffix E and ZA are not recommended for use in HDPE or PP Masterbatches with suffix E are not recommended for an addition rate lower than 2% and higher than 15%, they should also not be used in combination with UV stabiliser or calcium oxide desiccant Food contact - detailed information available on request 							
Polybatch 9035		Ivory	300°C	8	5	Yes	
Polybatch 6027		Beige	250°C	7-8	4	Yes	
Polybatch 1266		Beige	250°C	7-8	4	Yes	
Polybatch 1340		Brown	300°C	8	5	Yes	
Polybatch 1281		Brown	300°C	8	5	No	
Polybatch 1028		Brown	300°C	8	5	No	
Polybatch 8760		Grey	300°C	8	5	Yes	
Polybatch 8899		Grey	300°C	8	5	Yes	
Polybatch 8035		Grey	300°C	8	5	Yes	
Polybatch 8368		Grey	300°C	8	5	No	
Polybatch 8218		Grey	300°C	8	5	No	
Polybatch 7030		Silver	300°C	8	5	No	Metallic Silver
Polybatch 7010		Blue	300°C	8	5	No	Metallic Blue

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. Polybatch, Polyblak and Polywhite are trademarks owned and/or used by the LyondellBasell family of companies. Polybatch and Polyblak are registered in the U.S. Patent and Trademark Office.

Polybatch Material Standard Colors for Film Extrusion

Properties	Color	Heat stability ISO 12877-2	Light fastness ISO 4892-2	Weather Fastness ISO 4892-2	NIR Detectable	Specific Property Features	
<ul style="list-style-type: none"> Heat stability refers to 5% masterbatch addition in the respective carrier resin (ISO 12877-2, maximum color change of 4 according to Grey Scale ISO 105-A02, 5 minute dwell time) Light fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Blue Wool Scale ISO 102-B02, 8 = very good, 1 = very poor) Weather fastness refers to 5% masterbatch addition in the respective carrier resin (ISO 4892-2, measured according to Grey Scale ISO 102-A02, 5 = very good, 1 = very poor) NIR Detectable refers to 2% masterbatch addition in the respective carrier resin (internal method, polymer identification by near infrared spectroscopy) Masterbatches with suffix E and ZA are not recommended for use in HDPE or PP Masterbatches with suffix E are not recommended for an addition rate lower than 2% and higher than 15%, they should also not be used in combination with UV stabiliser or calcium oxide desiccant Food contact - detailed information available on request 							
<i>Polybatch</i> 7012		Green	300°C	8	5	No	Metallic Green
<i>Polybatch</i> 7060 E		Gold	240°C	7	3	No	Metallic Gold
<i>Polybatch</i> 7171		Gold	200°C	7	3	No	Metallic Gold
<i>Polybatch</i> 73622 NIR		Black	300°C	8	5	Yes	NIR detectable alternative to carbon black, semi-transparent
<i>Polyblak</i> 1423/20		Black	300°C	8	5	No	Carbon black, P-type
<i>Polyblak</i> 1850		Black	300°C	8	5	No	Carbon black, blue-tone, no food contact
<i>Polywhite</i> 8000		White	300°C	8	5	Yes	TiO ₂ , neutral undertone
<i>Polywhite</i> 8160		White	300°C	8	5	Yes	TiO ₂ , blue undertone
Standard Colors for PET - based on PET carrier resin							
<i>Polywhite</i> PT 8187		White	300°C	8	-	Yes	TiO ₂ , neutral undertone
Standard Colors for Polyamide - based on PA-6 carrier resin							
<i>Polywhite</i> PA 85848 VEG		White	300°C	8	-	Yes	TiO ₂ , neutral undertone

You can find out more about us by visiting our website at: www.lyondellbasell.com

Before using a LyondellBasell product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LyondellBasell product safely and legally. (Material Safety Data Sheets are available from LyondellBasell at www.lyondellbasell.com) This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LyondellBasell except in writing signed by an authorized LyondellBasell employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at LyondellBasell's option, and in no event shall LyondellBasell be liable for special, consequential, punitive, or exemplary damages. *Polybatch*, *Polyblak* and *Polywhite* are trademarks owned and/or used by the LyondellBasell family of companies. *Polybatch* and *Polyblak* are registered in the U.S. Patent and Trademark Office.